

VIASOL DECK 11a plus^{FF}

Parking deck coating system with separate membrane and wear coat with enhanced crack bridging properties (class B 3.2) for multi storey car parks for exposed and intermediate decks and sidewalks on bridges with pedestrian and vehicle traffic. In accordance with EN 1504-2 and DIN V 18026, class OS 11a / OS Fa.

Application Fields

Exposed car park decks and covered intermediate decks

Sidewalks on bridges

Roof decks with car traffic

System Build-up

LINE-MARKING

E.G. PU OR EPOXY



VIASOL PU-S650^{FF} OR

VIASOL PU-S6501P^{FF}

SEALER



VIASOL PU-L310^{FF}

(1 - 2 LAYERS)

WEAR COAT




VIASOL PU-L310^{FF}

ELASTIC
MEMBRANE



VIASOL EP-P210^{FF}

PRIMER



System Highlights

3.0 - 4.0 mm System thickness



Dynamic crack bridging B3.2



High abrasion resistance



Very high color and UV-stability with PU sealer



Good chemical resistance



Slip resistant surface for car traffic and pedestrian traffic



Available in many colours



Fire resistance class Bfl-s1



Class OS 11a, OS Fa
EN 1504-2
DIN V 18026

System Pictures






VIASOL DECK 11a plus^{FF}

Application and Consumption

SUBSTRATE REQUIREMENT

Substrate	Cementitious substrates according to the appropriate standards and approvals must be capable of bearing loads and be free of cracks and voids. Pull-off strength $\geq 1.5 \text{ N/mm}^2$, residual moisture content $< 4 \text{ \%CM}$, with higher residual moisture and on substrates with moisture from the backside special measures must be taken or a damp proof membrane must be installed. Substrate preparation e.g. grinding or shot blasting, sweeping and vacuum-cleaning is mandatory. Consumptions are calculated with VIASOL quartz sands and fillers. Usage of other quartz sands and fillers can cause changes of consumption and technical data.
Note	Detailed application instructions are available upon request or refer to the technical product data sheet.

Technical data

	property	standard	result
	Adhesive strength at T_{NORM}	DIN EN 1542	$\geq 3.1 \text{ N/mm}^2$ ($\geq 1.5 \text{ N/mm}^2$)
	Adhesive strength after freeze-thaw with deicing salt	DIN EN 13687-1 and -2	2.4 N/mm^2 ($\geq 1.5 \text{ N/mm}^2$)
	Dynamic crack bridging (-20°C)	DIN EN 1062-7	II T_{+V} (B3.2)
	Grip and slip resistant	DIN EN 13036-4 DIN 51130	57 Skt ($\geq 55 \text{ Skt}$) R11-V4 and R12-V6
	Chemical resistance	DIN EN 13529	Test liquids DiBT Nr. 1, 3, 10
	Abrasion resistance (H22 Rad)	DIN EN ISO 5470-1	2.100 mg /1000 U (≤ 3.000)
	Carbon dioxide permeability	DIN EN 1062-6	Class III $> 1.200 \text{ m}$ ($> 50 \text{ m}$)
	Water vapour permeability	DIN EN ISO 7783-1 und -2	Class III $> 200 \text{ m}$ ($> 50 \text{ m}$)
	Water absorption coefficient	DIN EN 1062-3	$< 0.01 \text{ kg/m}^2 \times \text{h}^{0.5}$ ($< 0,1$)
	Impact resistance	DIN EN ISO 6772-2	4 Nm – no cracks
	Fire behaviour class system	EN 13501-1	B _{if} -s1

Remark: for further information please refer to the product data sheets or contact our technical service. All data are approximate values. Therefore, no liability claims can be derived from the system data sheet. As all FLOORFINDER data sheets are updated on a regular basis it is the user's responsibility to obtain the most recent issue (see www.floorfinder.com.my or contact us directly) – all technical information is subject to change without prior notice. FLOORFINDER products are guaranteed against defective material and manufacture and are sold subject to its standard Terms and Conditions of Sale, copies which can be obtained on request.

Manufacturer:

FLOORFINDER ASIA SDN. BHD. – A division of VIACOR Polimer GmbH | No. 28, Lorong Sungai Puloh 1A/KU6 | Jalan Sungai Puloh | Batu 5 3/4 Kapar | 42100 Klang | Selangor Darul Ehsan | Malaysia | Tel: +603 3290 7644 | info@floorfinder.com.my | www.floorfinder.com.my
 Seite 2/2 Version Nr. 2 Stand: 07-2022